

## OEM PRICELIST

**AG141B  
BLACK SOFT DENSITY NEOPRENE CLOSED CELL SPONGE STRIPPING WITH  
ADHESIVE ON ONE SIDE**

(PRICES ARE PER ONE HUNDRED FEET)

**THICKNESS**

<b>WIDTH</b>	<b>1/16"</b>	<b>1/8"</b>	<b>3/16"</b>	<b>1/4"</b>	<b>5/16"</b>	<b>3/8"</b>	<b>1/2"</b>
1/2"	\$5.53	\$5.76	\$7.34	\$8.56	\$9.77	\$11.64	\$14.17
5/8"	\$6.55	\$7.43	\$8.89	\$10.36	\$11.81	\$14.07	\$17.14
3/4"	\$7.54	\$8.36	\$10.59	\$12.34	\$14.07	\$16.78	\$20.41
1"	\$10.44	\$11.65	\$13.63	\$16.37	\$18.19	\$21.95	\$26.58
1 1/4"	\$12.91	\$14.62	\$16.88	\$21.93	\$22.51	\$26.88	\$32.92
1 1/2"	\$15.64	\$17.59	\$20.25	\$24.40	\$27.88	\$32.26	\$39.53
2"	\$20.79	\$22.72	\$27.26	\$33.93	\$38.76	\$42.55	\$52.93
3"	\$31.02	\$32.86	\$41.70	\$48.68	\$55.61	\$65.07	\$78.99

ROLL LENGTH: 50 FEET

DISCOUNT SCHEDULE: UP TO \$500 - NET  
 \$500 - \$999.99 – LESS 5%  
 \$1,000 - \$2,499.99 – LESS 10%  
 \$2,500 & OVER – LESS 15%

MINIMUM ORDER: \$250.00  
 MINIMUM PER ITEM: \$100.00

F.O.B.: PHILADELPHIA, PA

LEAD TIME: 1-2 WEEKS

NOTE: MEDIUM AND FIRM DENSITY MATERIAL WILL BE QUOTED UPON REQUEST.

EFFECTIVE 12-5-2011

## TYPICAL PROPERTIES OF AG141B

POLYMER

NEOPRENE/EPDM/SBR

SPECIFICATIONS

ASTM D 1056-67 -----	SCE41
ASTM D 1056-78 -----	RE41
ASTM D 1056-85, 91, 98 -----	2A1
MIL-R-6130C TY/GR/CONDITION -----	II-A SOFT
MIL-C-3133C MIL STD 670 B -----	SCE3
UL 157/ UL 50/ UL 508-----	LISTED

FLAMMABILITY SPECIFICATIONS

UL-94-HF-1 -----	LISTED
UL-94-HBF -----	PASS
MIL-R-6130C -----	PASS
FMVSS-302 -----	PASS

Physical Property	Test Method	Unit of Measure	Result
COMPRESSION DEFLECTION @25%	ASTM D 1056	psi kPa	2-5 14-35
DENSITY	ASTM D 3575	pcf g/cm <sup>3</sup>	4-8 .064-.128
WATER ABSORPTION MAX. WEIGHT CHANGE	ASTM D 1056	%	5
TEMPERATURE RANGE	N/A	<sup>0</sup> F	-40 TO + 200
HIGH INTERMITTENT	N/A	<sup>0</sup> F	+250
TENSILE STRENGTH	ASTM D 412 (DIE A)	psi kPa	75 517
ELONGATION MINIMUM	ASTM D 412 (DIE A)	%	150
ACCEL. AGING (7 DAYS @ 158 <sup>0</sup> F) FLEXIBILITY (NO CRACKING) APPEARANCE CHANGE CHANGE IN COMPRESSION DEFLECTION	ASTM D 1056	N/A 180 <sup>0</sup> BEND N/A %	PASS NONE ±30
THERMAL CONDUCTIVITY	ASTM C 177-85	K FACTOR	.30
COLOR	N/A	N/A	BLACK

**RESISTANCE TO:**

ACID	EXCELLENT	OZONE	EXCELLENT
ALKALI	EXCELLENT	KETONES	FAIR
GASOLINE AND OIL	FAIR	CHLORINATED SOLVENTS	POOR
AROMATIC HYDROCARBONS	FAIR	OXIDATION	EXCELLENT

This information is furnished as a guide for selecting materials. Atlantic Gasket disclaims liability for results or use this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

4/21/03