

January, 2011

3M™ Double Coated Tape 92015

Product Description

3M™ Double Coated Tapes with 3M™ Adhesive 200MP feature a thin polyester film for dimensional stability and improved handling with ease of die-cutting and laminating. The 3M adhesive 200MP provides exceptional temperature and chemical resistance.

Product Features

- A thin polyester carrier in the products provides dimensional stability and improved handling with ease of die-cutting and lamination compared to adhesive transfer tapes.
- 3M™ Adhesive 200MP provides exceptional temperature and chemical resistance and withstands tough application environments.



3M™ Double Coated Tape 92015

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Notes
Total Tape Thickness without liner	0.15 mm	5.9 mil	
Faceside Adhesive Thickness	0.069 mm	2.7 mil	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Backside Adhesive Thickness	0.069 mm	2.7 mil	Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Carrier Thickness	0.012 mm	0.5 mil	
Faceside Adhesive Type	200MP		Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Backside Adhesive Type	200MP		Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Adhesive Carrier	Clear Polyester		
Liner	58# Polycoated Kraft		
Liner Thickness	0.11 mm	4.2 mil	
Liner Color	Tan		

Typical Performance Characteristics

Property	Values	Method	Test Condition	Notes
Additional Test notes	Not recommended for low energy plastics (polypropylene, polyethylene). For these surfaces, please refer to 3M™ Adhesive 300, 300LSE, 350, 360 and 300MP.			
Static Shear	>10,000 min	ASTM D3654	1000 g @ Room Temperature	1 in ² sample size
Static Shear	>10,000 min	ASTM D3654	500 g @ 70°C (158°F)	1 in ² sample size

Relative High Temperature Operating Ranges		Test Condition
149 °C	300 °F	Short Term (minutes, hours)
121 °C	250 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

180° Peel Adhesion		Dwell/Cure Time	Substrate
7.7 N/cm	70 oz/in	15 min @ Room Temperature	Stainless Steel
8.2 N/cm	75 oz/in	15 min @ Room Temperature	Polycarbonate (PC)
6.6 N/cm	60 oz/in	15 min @ Room Temperature	ABS
2.2 N/cm	20 oz/in	15 min @ Room Temperature	Polypropylene (PP)
16.4 N/cm	150 oz/in	72 hr @ Room Temperature	Stainless Steel
10.4 N/cm	95 oz/in	72 hr @ Room Temperature	Polycarbonate (PC)
8.8 N/cm	80 oz/in	72 hr @ Room Temperature	ABS
2.7 N/cm	25 oz/in	72 hr @ Room Temperature	Polypropylene (PP)

Property: 180° Peel Adhesion
 Method: ASTM D3330
 Backing: Aluminum Foil

Available Sizes

Property	Values	
Note	Subject to Minimum Order Requirements	
Maximum Available Width	54 in	
Normal Slitting Tolerance	± 0.8 mm	± 1/32 in
Core Size (ID)	76.2 mm	3 in

Maximum Length		Width
132 m	144 yd	1/4 in to 1 in widths
329 m	360 yd	1 in to 54 in

Property: Maximum Length

Electrical and Thermal Properties

Property	Values
Breakdown Voltage	7600 V
Dielectric Strength	1300 V/mil

Environmental Performance

Humidity Resistance: High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance: When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

Water Resistance: Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

Temperature Cycling Resistance: High bond strength is maintained after cycling four times through:

4 hours at 158°F (70°C)

4 hours at -20°F (-29°C)

4 hours at 73°F (22°C)

Chemical Resistance: When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids, and alkalis.

Handling/Application Information**Application Ideas**

- Graphic overlays
- Nameplates
- Appliques
- Decorative Trim
- Thermal and sound damping applications in the electronics and appliance industry.
- Attachment to plastics, (ABS, PC).

Handling/Application Information (continued)

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*

*Note: Carefully read and follow the manufacturer's precautions and directions for use when using solvents. Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Storage and Shelf Life

Store in original cartons at 70°F (21°C) and 50% relative humidity.

If stored under proper conditions, this product retains its performance and properties for 24 months from date of manufacture.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Trademarks

3M is a trademark of 3M Company.

3M™ Double Coated Tape 92015

References

Safety Data Sheet (SDS)

https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=92015

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Adhesives and Tapes Division
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2019. All Rights Reserved.

The brands listed above are trademarks of 3M