

November, 2013

3M™ Membrane Switch Product with Adhesive 200MP 9057MP


Product Description

3M™ High Performance Acrylic Adhesive 200MP is a popular choice and industry standard, for graphic attachment and general industrial joining applications. It provides outstanding adhesion to metal and high surface energy plastics. This adhesive provides some initial repositionability for placement accuracy when bonding to plastics. It also performs well after exposure to humidity and hot/cold cycles and provides the assurance the switch will perform through difficult environmental conditions and millions of actuations.

Product Features

- Up to 400°F short-term heat resistance
- Excellent solvent resistance
- Excellent shear strength to resist slippage and edge lifting

3M™ Double Coated Membrane Switch Spacers feature 2.0 or 5.0 mil adhesive layers for industry-standard, high-performance requirements.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Notes
Faceside Adhesive Thickness	0.05 mm	2 mil	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Backside Adhesive Thickness	0.05 mm	2 mil	Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Carrier Thickness	0.08 mm	3 mil	
Adhesive Carrier	Polyester Film (PET)		
Adhesive Thickness	0.05 mm	2 mil	
Primary Liner Type	94# Polycoated Kraft Paper (PCK)		Inner liner is primary(stays with die-cut part); Outer liner is secondary (removed first)
Secondary Liner Type	94# Polycoated Kraft Paper (PCK)		Inner liner is primary(stays with die-cut part); Outer liner is secondary (removed first)
Primary Liner Thickness	0.18 mm	7 mil	
Secondary Liner Thickness	0.18 mm	7 mil	

Typical Performance Characteristics

90° Peel Adhesion		Dwell/Cure Time	Substrate
5.9 N/cm	54 oz/in	Initial	Stainless Steel
10 N/cm	95 oz/in	72 hr @ Room Temperature	Stainless Steel
16.7 N/cm	153 oz/in	72 hr @ 158°F(70°C)	Stainless Steel
7.2 N/cm	66 oz/in	Initial	Aluminum
8 N/cm	73 oz/in	72 hr @ Room Temperature	Aluminum
16.2 N/cm	148 oz/in	72 hr @ 158°F(70°C)	Aluminum
4 N/cm	37 oz/in	Initial	PET

Table continued on next page

Typical Performance Characteristics (continued)

90° Peel Adhesion		Dwell/Cure Time	Substrate
6.6 N/cm	60 oz/in	72 hr @ Room Temperature	PET
14.9 N/cm	136 oz/in	72 hr @ 158°F(70°C)	PET
4.5 N/cm	41 oz/in	Initial	Polycarbonate (PC)
7.2 N/cm	66 oz/in	72 hr @ Room Temperature	Polycarbonate (PC)
7.9 N/cm	72 oz/in	72 hr @ 158°F(70°C)	Polycarbonate (PC)

Property: 90° Peel Adhesion
 Method: ASTM D3330 (modified)
 Backing: PET Film

Dynamic Shear		Substrate
0.55 MPa	79 lb/in ²	Stainless Steel
0.46 MPa	66 lb/in ²	Polycarbonate (PC)

Property: Dynamic Shear
 Method: ASTM D1001
 Backing: PET Film

Property	Values	Method	Substrate	Backing	Test Condition	Notes
Tensile Strength	5062 lb/in	ASTM D2370	Stainless Steel	PET Film		
Static Shear	10,000+ min	ASTM D3654	Stainless Steel	PET Film	1000 g @ Room Temperature	0.5 in ²
Static Shear	10,000+ min	ASTM D3654	Stainless Steel	PET Film	500 g @ 70°C (158°F)	0.5 in ²

Electrical and Thermal Properties

Property	Values	Method	Test Condition	Notes
Insulation and Moisture Resistance	1.1 × 10 ¹³ Ω	Mil-I-46058C	100VDC, 60 sec	
Dielectric Constant	3.33	ASTM D150	Room Temperature	
Dissipation Factor	0.013	ASTM D150		
Dielectric Strength	1700 V/mil	ASTM D149		Short time method (air)

Table continued on next page

Electrical and Thermal Properties (continued)

Property	Values	Method	Test Condition	Notes
Volume Resistivity	$1.3 \times 10^{15} \Omega\text{-cm}$	ASTM D257	Room Temperature	
Surface Resistivity	$>5.6 \times 10^{16} \Omega$	ASTM D257	Room Temperature	
Coefficient of Thermal Expansion	$5.4 \times 10^{-4} \text{ m/m/}^\circ\text{C}$	ASTM D696	First Heat(125 - 175°C)	

Environmental Performance

Humidity Resistance – High humidity has a minimal effect on adhesive performance. Bond strength shows no significant reduction after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance – When properly applied, nameplates and decorative trim parts are not adversely affected by outdoor exposure.

Water Resistance – Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

Temperature Cycling Resistance – High bond strength is maintained after cycling four times through:

4 hours at 158°F (70°C)

4 hours at -20°F (-29°C)

4 hours at 73°F (22°C)

Chemical Resistance – When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.

Bond Build-up: The bond strength of 3M™ High Performance Acrylic Adhesive increases as a function of time and temperature as the adhesive further wets the surface and reaches maximum bond strength after 72 hours at room temperature.

Temperature/Heat Resistance: 3M™ High Performance Acrylic Adhesive on polyester carriers is usable for short periods (minutes, hours) at temperatures up to 300 °F (149°C) and for intermittent longer periods (days, weeks) up to 250°F (121°C).

Lower Temperature Service Limit: -40°F (-40°C).

Handling/Application Information

Application Ideas

- 3M™ Double Coated Membrane Switch Spacers are ideal for circuit separation

Storage and Shelf Life

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity. If stored properly, product retains its performance and properties for 24 months from date of manufacture.

3M™ Membrane Switch Product with Adhesive 200MP 9057MP

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Trademarks

3M is a trademark of 3M Company

References

Safety Data Sheet (SDS)

https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9057MP

Family Group

	7953MP	7956MP	7957MP	7959MP	7961MP	9045MP	7945MP	9057MP	9059MP	9061MP	7993MP	7995MP	7997MP	9056MP
Faceside Adhesive Thickness (mm)	0.04	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05				0.05
Backside Adhesive Thickness (mm)	0.04	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05				0.05
Carrier Thickness (mm)	0.01	0.05	0.08	0.13	0.18	0.03	0.03	0.08	0.13	0.18	0.03	0.08	0.13	0.05
Adhesive Carrier	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)	Polyester Film (PET)

Table continued on next page

3M™ Membrane Switch Product with Adhesive 200MP 9057MP

Family Group (continued)

	7953MP	7956MP	7957MP	7959MP	7961MP	9045MP	7945MP	9057MP	9059MP	9061MP	7993MP	7995MP	7997MP	9050MP
Adhesive Thickness (mm)	0.04	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Primary Liner Type	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)				94# Polycoated Kraft Paper (PCK)
Secondary Liner Type	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)	58# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)	94# Polycoated Kraft Paper (PCK)				94# Polycoated Kraft Paper (PCK)
Primary Liner Thickness (mm)	0.11	0.11	0.11	0.11	0.11	0.18	0.11	0.18	0.18	0.18				0.18
Secondary Liner Thickness (mm)	0.11	0.11	0.11	0.11	0.11	0.18	0.11	0.18	0.18	0.18				0.18

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Recognition/Certification

TSCA: This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements MSDS: 3M has not prepared a MSDS for this product which is not subjected to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, this product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards. UL: These products have been recognized by Underwriters Laboratories, Inc. under UL 746C and UL 969. For more information on the UL Certification, please visit the website at <http://www.3M.com/converter>, select UL Recognized Materials, then select the specific product area. Note: One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at 3M.com/regs.

