

April, 2014

3M™ High Performance Acrylic Adhesive 467MC

Product Description

3M™ 467MC features a 200MP laminating adhesive on a 3M proprietary liner, which creates micro-channels in the adhesive surface (back side surface of adhesive). The crosshatched pattern creates a continuous and permanent network of micro-channels in the back side of the adhesive, allowing air to escape from between the adhesive surface and the substrate. This helps to facilitate bubble free laminations of graphics to substrates.

3M™ Adhesive 200MP is a popular choice for graphic attachment and nameplate applications because it has excellent quality, consistency and durability. In addition, as a result of 3M's innovative, proprietary process, 3M adhesive 200MP also offers the following excellent performance characteristics.



Product Features

- Clarity (virtually free of vapor inclusions that are commonly found in adhesives produced by the traditional solvent coating technique).
- Excellent high temperature performance as well as excellent shear strength (that minimizes edge lifting and slippage of parts).
- Excellent resistance to harsh environments; this adhesive can withstand splashes of organic solvents, weak acids and bases and salt water, cleaning solutions, germicides, disinfectants, oils, etc. In addition, it performs well after exposure to humidity and hot/cold cycles.
- Provides some initial repositionability when bonding to plastic parts (not metal) which allows graphic parts to be lifted and repositioned if initial alignment is incorrect.
- Adhesive family is provided with a polyester and PCK liner configurations to help ensure excellent process flexibility.

3M™ High Performance Acrylic Adhesive 467MC

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	
Adhesive Type	200MP	
Adhesive Thickness	0.05 mm	2 mil
Liner	58# PCK	

Typical Performance Characteristics

90° Peel Adhesion		Dwell/Cure Time
6.6 N/cm	60 oz/in	15 min @ Room Temperature
11.3 N/cm	103 oz/in	72 hr @ Room Temperature

Property: 90° Peel Adhesion
Method: ASTM D3330
Backing: Aluminum Foil

Static Shear	Test Condition
10,000+ min	2000 g @ Room Temperature
10,000+ min	1000 g @ 93°C (200°F)
10,000+ min	500 g @ 177°C (350°F)

Property: Static Shear
Method: ASTM D3654
Substrate: Stainless Steel
Backing: Aluminum Foil
notes: 1 in x 1 in sample area, Test terminated after 10,000 minutes

Storage and Shelf Life

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity. If stored properly, product retains its performance and properties for 18 months from date of manufacture.

3M™ High Performance Acrylic Adhesive 467MC

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Trademarks

3M is a trademark of 3M Company.

References

Safety Data Sheet (SDS)

https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=467MC

Family Group

	467MC	468MC	467MCF	468MCF
Adhesive Type	200MP	200MP	200MP	200MP
Adhesive Thickness (mm)	0.05	0.127	0.05	0.127
Liner	58# PCK	58# PCK	PET	PET

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Bottom Matter Images

[Image 4] [Image 5]

