

ATLANTIC GASKET CORP.

3908 Frankford Avenue Philadelphia, PA 19124 USA

Phone: 215-533-6400 Fax: 215-533-4130

www.atlanticgasket.com sales@atlanticgasket.com

NI-2085

Nonasbestos Gasket Material

F723940E43M6

Description:

NI-2085 has a nitrile butadiene rubber binder for resistance to water, coolant, oil and fuel. It has excellent strength and sealability characteristics, and is intended for applications with short duration maximum temperatures up to 190°C (375°F). NI-2085 has UL component recognition.

Property:

Specification:

Method:

Density, g/cc(lb/cu.ft)	1.36 (85) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	10 - 20	ASTM F 36
Recovery, %	50 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	13.79 (2000) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Tensile Strength, %	35 (max.)	
Change in Thickness, %	10 (max.)	
Change in Weight, %	30 (max.)	
Change in Compressibility, %	25 (max.)	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	15 (max.)	
Change in Weight, %	30 (max.)	

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Atlantic Gasket Corp. shall not be liable for any damages arising out of the use of any of its guide specifications.