

ATLANTIC GASKET CORP.
3908 Frankford Avenue Philadelphia, PA 19124 USA
Phone: 215-533-6400 Fax: 215-533-4130
www.atlanticgasket.com sales@atlanticgasket.com

TN-9004
Nonasbestos Gasket Material
F729100E33M9

Description:

TN-9004 is a heavy-duty, high density material with fully cured nitrile butadiene rubber binder. It has excellent resistance to fuel and oil, and has good tensile strength. It is intended for applications with high flange pressures with short duration maximum temperatures up to 350°C (650°F).

Property:	Specification:	Method:
Density, g/cc(lb/cu.ft)	1.52 (95) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	5 - 20	ASTM F 36
Recovery, %	45 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	17.24 (2500) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Tensile Strength, %	45 (max.)	
Change in Thickness, %	15 (max.)	
Change in Compressibility, %	25 (max.)	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	15 (max.)	
Change in Weight, %	20 (max.)	
Binder Type	Fully Cured Nitrile Butadiene	

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Atlantic Gasket Corp. shall not be liable for any damages arising out of the use of any of its guide specifications.